

TECHNICAL DATA FOR QUARTZ BASED ENGINEERED STONES

Product:	HELSINKI
Brand name:	SM QUARTZ®
Composition:	7 - 10 % Resin, 90 - 93 % Quartz
Surface finish:	Polished, Silk
Slabs size (cm):	320x155, 330x165
Slabs thickness* (cm):	2,0 - 3,0



* Other sizes and thicknesses available on request

Characteristics	Standard	Value	Notes
Apparent density	EN 14617-1	2350 - 2450 Kg/m ³	
Water absorption	EN 14617-1	≤ 0,10 %	
Flexural strength	EN 14617-2	28 - 45 Mpa	
Abrasion resistance	EN 14617-4	27 - 29 mm	
Frost resistance	EN 14617-5	KM _{f25} 0,9 - 1,2	
Thermal shock resistance	EN 14617-6	Δm% ≤ 0,07 %	Test temperature: 70°C
		ΔR _{f,20} ≤ 20 %	
Impact resistance	EN 14617-9	1,5 - 2,5 J	For thickness 12 mm
		≥ 3,0 J	For thickness 20 mm, 30 mm
Chemical resistance	EN 14617-10	C4	
Linear thermal expansion coefficient	EN 14617-11	21 - 32 x 10 ⁻⁶ °C ⁻¹	
Dimensional stability	EN 14617-12	Classe A (<0,3 mm)	Referred to tiles 30x30x1,2 cm
Electrical resistivity	EN 14617-13	ρ _s ≥ 10 ¹⁰ Ω	Referred to surface
		ρ _v ≥ 10 ⁸ Ω m	Referred to volume
Compression resistance	EN 14617-15	150 - 250 MPa	
Mohs hardness	EN 101	up to 7 Mohs	
Thermal conductivity	EN 12524	1,3 W/(m K)	From tabulated values
Reaction to fire	ASTM E84	Class A	US standard
Reaction to fire	EN 13501-1	A2-s2,d0	Walls
Reaction to fire	EN 13501-1	A2 _f -s1	Flooring
Slip resistance	EN 14231	≥ 35 (Dry)	
		≥ 3 (Wet)	
Slip resistance	DIN 51130	R9	For Honed H9